

Alpiplast KG  
J. Kravogl Str 10  
Gewerbegebiet Töll  
39020 Partschins (BZ)  
ITALY

Eurofins Product Testing A/S  
Smedskovvej 38  
8464 Galten  
Denmark

CustomerSupport@eurofins.dk  
www.eurofins.com

## Migration Report

23 September 2021

### 1 Sample Information

Sample name	Drinking straw Bio Eco all colors
Sample reception	13/08/2021
Sample no.	392-2021-00403106
Analysis period	25/08/2021 - 22/09/2021

### 2 Brief Evaluation of the Results

Type of analysis	Conclusion	Regulation or protocol
Overall migration	Pass	(EU) No 10/2011

Full details based on the testing and direct comparison with limit values are available in the following pages



Catja Foged Wittrup  
Analytical Chemist



Brian Jensen  
MSc. Chemistry

### 3 Applied Test Methods

#### 3.1 General Test References

Method	Parameter	Analysis principle	LOD	Um(%)
NMKL 86 <sup>1</sup>	Aerobic Plate Count 30°C	E-Cultural technique (non-chromogenic media)	10 cfu/g	-
NMKL 98 <sup>1</sup>	Yeasts & Moulds	E-Cultural technique (non-chromogenic media)	10 cfu/g	-
EN 1186-3:2002	Preparation for migration	Exposure to 3% acetic acid by total immersion	-	-
EN 1186-1:2002	Overall migration into 3% acetic acid	Gravimetry	1 mg/dm <sup>2</sup>	20%
EN 1186-3:2002	Preparation for migration	Exposure to 50% ethanol by total immersion	-	-
EN 1186-1:2002	Overall migration into 50% ethanol	Gravimetry	1 mg/dm <sup>2</sup>	20%
EN 1186-3:2002	Preparation for migration	Exposure to demineralised water by total immersion	-	-
EN 1186-1:2002	Overall migration into water	Gravimetry	1 mg/dm <sup>2</sup>	20%
EN 1186-2:2002	Preparation for migration	Exposure to olive oil by total immersion	-	-
EN 1186-1:2002	Overall migration into olive oil	Gravimetry	2 mg/dm <sup>2</sup>	30%

#### 3.2 Test Conditions

Simulant	Technique	Area exposed	Volume (Simulant)	Migration Conditions
		[dm <sup>2</sup> ]	[mL]	
3% acetic acid	Immersion	2.1	100	24 Hours at 40°C
50% ethanol	Immersion	2.1	100	24 Hours at 40°C
Demineralised water	Immersion	2.1	100	24 Hours at 40°C
Olive oil	Immersion	2.0	100	24 Hours at 40°C

<sup>1</sup> Eurofins Steins Laboratorium A/S : DS EN ISO/IEC 17025 DANAK 222

\*: Not accredited

<: Less than

>: Greater than

LOD: Limit of detection

⊠: Internal test method

n.d: Not detected

n.m: Not measurable

LOQ: Limit of quantification

Um(%): The expanded uncertainty Um(%) equals 2 x RSD%. For further information please visit [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty)

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

## 4 Results

### 4.1 Overall migration

Simulant	Single determinations			Average	OML value
	[mg/dm <sup>2</sup> ]	[mg/dm <sup>2</sup> ]	[mg/dm <sup>2</sup> ]		
3% acetic acid	< 1	< 1	< 1	< 1	10
50% ethanol	< 1	< 1	< 1	< 1	10
Demineralised water	< 1	< 1	< 1	< 1	10
Olive oil	< 2	< 2	< 2	< 2	10

### 4.2 Microbial Analysis

Parameter	Result
	[cfu/g]
Aerobic Plate Count 30°C	< 10
Yeasts & Moulds	< 10

## 5 Summary and Evaluation of the Results

The results for overall migration **are below** the threshold value of 10 mg/dm<sup>2</sup>.

Consequently, the product tested **complies** with the requirements in Commission Regulation (EU) No 10/2011 with amendments up to and including Commission Regulation (EU) 2020/1245 on plastic materials and articles intended to come into contact with food for the above mentioned test conditions.

### 5.1 Decision Rules

Eurofins Product Testing A/S, declare statement of conformity based on the “Binary Statement for Simple Acceptance Rule” described in ILAC’s “Guidelines on decision Rules and Statements of Conformity” ILAC-G8:09/2019.

This means that results above the detection limit are always reported with two significant digits. Results are evaluated with the same number of significant digits as the corresponding limit values, and conformity is based on results being less than or equal to limit values.

For further information please visit [www.eurofins.dk/product-testing/om-os/beslutningsregler/](http://www.eurofins.dk/product-testing/om-os/beslutningsregler/)

\*: Not accredited

<: Less than

>: Greater than

LOD: Limit of detection

Um(%): The expanded uncertainty Um(%) equals 2 x RSD%. For further information please visit [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty)

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

⌘: Internal test method

n.d: Not detected

n.m: Not measurable

LOQ: Limit of quantification

## 6 Picture of Sample



## 7 Version History

Report date	Report number	Modification
23/09/2021	392-2021-00403106_MP_EN	Current version

\*: Not accredited

<: Less than

>: Greater than

LOD: Limit of detection

Um(%): The expanded uncertainty Um(%) equals 2 x RSD%. For further information please visit [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty)

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

⊠: Internal test method

n.d: Not detected

n.m: Not measurable

LOQ: Limit of quantification